



Perf Go Green

10/28/2009

3192628

11:09:50 AM

Test ID:	Typical Use	Load:	Cycle:	Est. Life (days):	Reported in:	Reporting Cut-Off:	Duracell Coppertop	Energizer Max	Fuji EnviroMax	Perf Go Green
C181MAA4	Toy	3.9 Ohm	1hpd	8	Hours	0.8	START: 10/20/09 Complete: 10/28/09	START: 10/20/09 Complete: 10/27/09	START: 10/20/09 Complete: 10/27/09	START: 10/20/09 Complete: 10/27/09

C181MAA4	Duracell	Energizer	Fuji	Perf Go Green
Loading Cycle:	Toy - 3.9 Ohm 1hpd			
Cut-off Voltage:	0.8			
Battery Size:	AA			
Time Calculated in:	Hours			
Average	7.9	7.7	7.3	7.3
Std.Dev.	0.4	0.0	0.1	0.1
Minimum	6.8	7.6	7.0	7.2
Maximum	8.3	7.8	7.4	7.4
x-3sd	6.6	7.5	6.9	7.2
x+3sd	9.2	7.8	7.7	7.5
Count	9	9	9	9
Test Start Date:	10/20/09	10/20/09	10/20/09	10/20/09
Test Finish Date:	10/28/09	10/27/09	10/27/09	10/27/09
Days on Test:	8	7	7	7
Channel #	Loading Time to Reach Cut-off Voltage			
1	7.9	7.7	7.4	7.4
2	8.0	7.7	7.3	7.4
3	8.0	7.7	7.3	7.4
4	8.2	7.6	7.4	7.4
5	8.3	7.8	7.0	7.4
6	7.8	7.7	7.3	7.2
7	6.8	7.7	7.3	7.4
8	7.8	7.6	7.3	7.3
9	8.2	7.7	7.4	7.3