




**Comparison PerfPower pre 6/11 vs Duracell vs PerfPower post 6/11**

<b>Subject</b>	<b>Batteries Performance Comparison For GOGREEN&amp;Duracell</b>		
<b>Chief Tester</b>	<i>Zulib</i>	<b>Issue Date</b>	2010-5-25

**1. Sample Information**



**2. Discharge Performance(At 20±2°C , RH 45 ~ 75 %)**

Type	Discharge conditions	GO GREEN	Duracell	PerfPower 6/11
LR20	1.5Ω, 4m/h,8h/d-0.9V (h)	13.7	14.1	13.9
	2.2Ω, 1h/d-0.8V (h)	23.7	25.0	24.1
	10Ω, 4h/d-0.9V (h)	119.2	118.6	125.0
	600mA, 2h/d-0.9V (h)	15.4	16.7	16.1
	2.2Ω, 24h/d-0.9V (h)	15.3	20.4	19.0
LR14	400mA, 2h/d-0.9V (h)	13.1	13.2	12.2
	3.9Ω, 1h/d-0.8V (h)	23.3	23.2	21.6
	20Ω, 4h/d-0.9V (h)	131.7	120.5	121.3
	3.9Ω, 4m/h,8h/d-0.9V (h)	21.9	20.1	20.0
	3.9Ω, 24h/d-0.9V (h)	17.8	18.2	18.0
6LR61	620Ω, 2h/d-5.4V (h)	30.4	49.2	47.9
	10KΩ+620Ω, 1s/d 24h/d-7.5V(day)	6.6	21.8	20.0
	270Ω, 1h/d-5.4V (h)	18.4	20.8	20.0
	35mA, 24h/d-5.4V (h)	13.1	14.6	15.3